

SILICONE

DESCRIPTION: Silicone based, matt, water based, first class exterior paint.

CHARACTERISTIC:

- Water resistant, adhesive, modified by silicone exterior topcoat paint.
- No swelling or scraps through its silicone structure.
- Resistant against rain, snow, and UV.
- High resistant against corrosion on surfaces particularly near sea.

APPLICATION SURFACES:

Can be applied on exterior surfaces such as plaster, concrete finishes and similar surfaces.

TECHNICAL INFORMATION:

Consumption: Single coat: 12- 14 (ml/lt) ; Double coat : 5 - 6 (ml/lt)

Thinner: Water

Thinning Ratio: % 10-15

Density: 1,53 ± 0,02 (g / cmi)

Drying: Touch dry: after 15-20 minutes, Dust repulsive: after 1 hour, hard dry: after 24 hours

Viscosity: 115 KU ± 10 (23 e C)

pH: 8 – 8,5

Brilliance: at 85e 7 ± 3

Thickness of dry coat: (40 ± 5) micron

Thickness of wet coat: (90 ± 5) micron

SURFACE PREPARATION:

- The surface should be free from all kind of dust. Loose and old paintings should be scraped and surface should be dry.
- After hollows and cracks should be filled with Silkcoat Exterior Acrylic Putty, Silkcoat Primer is applied.

APPLICATION:

- Silicone should be thinned % 10- 15 with water, and applied in 2 coats with roller, brush or spay gun.
- Leave minimum 2 hours between coats depending on weather conditions.
- After application, tools should be cleaned with water.

APPLICATION DETAILS:

- On new painted surfaces, make sure that surface has waited about 28 days before application.
- Before application Silicone should be completely mixed so that it is homogenous.
- Do not apply below 5 C.
- Gloss and glasslike surfaces should be rubbed before application to obtain better adhesive and a healthy surface .

CAUTION:

- Avoid getting eye and skin contact. In case wash with plenty of water.
- Preserve in a tightly closed container.
- Keep above the reach of children
- Do not dump into sewer system.

STORAGE:

Keep at a cool and clean place away from sun light. It can be stored unopened 1 year at room temperature.

PACKAGING:

15 lt, 2,5 lt PE Bucket

QUALITY CERTIFICATE:

Found complying as per TS 7847 conditions.
ISO 9001-2008